

| Product data sheet and technical information parquet floors base.59 | |
|---|---------|
| Product range | base.59 |





| Product data | | |
|------------------------------|---|------------------------------|
| | plank | 3 strip |
| Dimensions in mm (L * W * T) | 2190 x 162 x 11 | 2390 x 200 x 11 |
| Wear surface | ≥ 2,5 mm | ≥ 2,5 mm |
| Units / package | 8 pieces | 8 pieces |
| Package | 2,838 m ² , 14,85 kg | 3,824 m ² , 20 kg |
| Warranty | 15 years for private use according to our terms of warranty | |
| Connection | ClickTec | |
| Notes | Subject to technical changes, Cleaning and care see instructions please | |

| Product constructions | | |
|-----------------------|-----------------|-----------------|
| Wear surface | Hardwood | Hardwood |
| Middle layer | softwood staves | softwood staves |
| Stabilizing layer | pine veneer | pine veneer |

| Product properties | | | |
|-----------------------------|---------------|--------------------------|---|
| | Test norm | | |
| Thermal resistance | DIN EN 4108-4 | 0,078 m ² K/W | 0,078 m ² K/W |
| Thermal conductivity | EN 12664 | ≥ 0,091 W/(m*K) | ≥ 0,091 W/(m*K) |
| Biological durability | | | class 1 |
| PCP content | | | < 5 ppm |
| Formaldehyde emission | EN 717 - 2 | | E1 |
| Reaction to fire | EN 13501-1 | | Dfl-s1 |
| Resistance to chair castors | DIN EN 13329 | | No impact if soft chair castors are used |
| Sorting requirements | EN 13489 | | Requirements are met by factory sorting |
| Laying system | EN 13489 | | floating, overall glued |
| Floor heating | | | Only suitable for hot water underfloor heating with a maximum surface temperature of 29°C |
| Renovation | | | At least resandable twice with normal wear |
| Disposal | | | Private disposal in the garbage possible |

| Tolerances according to EN 13489 | |
|-----------------------------------|----------|
| allowed differences in width | ± 0,2 mm |
| allowed differences in squareness | ≤ 0,2 % |
| longitudinal curvature | ≤ 0,1 % |
| Transverse curvature | ≤ 0,2 % |
| Differences in height | ≤ 0,2 mm |
| Humidity level on delivery | 5-9% |

| Surface properties | | | | |
|------------------------|-----------------|----------|---------------------|------------------------------|
| | Test norm | laquered | natural oil treated | natural oil treated, brushed |
| slip resistance | EN 15676 | USRV 70 | USRV 57 | USRV 94 |
| Resistance to staining | DIN 68861 - 1 | 1B | 1C | 1C |
| Scratch resistance | Hamberger Hobel | ≥ 20 N | n.n | n.n |

| Product identification | | | |
|---|---|---|---|
|  |  |  |  |